

Material test report NBR 70

Colour Black

Property	Unit	Test method	Test parameter	Value
Hardness	IRHD	ASTM D 1415		70 ±5
Tensile strength	MPa	ASTM D 412		14,4
Ultimate elongation	%	ASTM D 412		389
Specific gravity	g/cm ³	ASTM D 297		1,28 ±0,03
Compression set	%	ASTM D 395 B	22h / 100°C	11
Low temp. resistance	°C	ASTM D 2137	brittleness no cracks after 3 min. at	-40
Low temp. resistance	°C	ASTM D 1329	TR10	-26,4

Changes of properties after ageing

Medium	test method	Time	Temperature	Hardness points	Tensile strength	Ultimate elongation	Volume
		H	°C		%	%	%
Air	ASTM D 573	70	100	+3	+1	-7	
ASTM IRM oil 901	ASTM D 471	70	100	+4	-5	-4	-5
ASTM IRM oil 903	ASTM D 471	70	100	-3	-12	-11	+8
Fuel A	ASTM D 471	70	23	-2	-13	-6	+2
Fuel B	ASTM D 471	70	23	-11	-31	-21	+21

Material approvals:

DVGW DIN EN 549 H3/B2 (-20...+80°C)

The above indicated data were determined to the best knowledge according to modern laboratory standards on standardised test specimen. If these data are compared with data which were determined on finished parts it may come to variations.